



SOCIAL SECURITY

MEMORANDUM

Date: 05/13/08

To: Lollie Driulini
Social Security Administration

From: Rick Prieto
SSA Facilities Team Dallas, TX

Subject: Initial Asbestos Inspection Report for The Poteau, OK SSA District Office

Attached is a copy of the U.S. Public Health Service's (PHS) Initial Asbestos Inspection Report for the SSA office located at 1306 Tarby Road, Poteau, OK 74953. Laboratory analytical results indicated that asbestos was not detected in any of the building materials sampled during this inspection. As a result no further action is necessary. A copy of this report should be saved as long as necessary to document this inspection.

If you have any questions, please call me at 214-767-3104 in Management and Operations Support.

Thank You,

Rick Prieto



SOCIAL SECURITY

MEMORANDUM

Date:

APR 24 2008

To: Ricardo Prieto, Field Services Specialist
Region VI

From: Tara Barker, Industrial Hygienist
Office of Environmental Health
and Occupational Safety

Subject: Asbestos Initial Inspection Report for the SSA Poteau Field Office (E32) --INFORMATION

Attached is a copy of the U.S. Public Health Service's (PHS) Asbestos Inspection Report for the SSA Poteau Field Office located at 1306 Tarby Road, Poteau, OK 74953. We have reviewed this report and concur with the findings and recommendations. No asbestos-containing material was identified during this inspection. A copy of this report should be maintained for as long as necessary to document the inspection.

Please forward a copy of this report to the SSA field office manager, the local GSA representative, and your regional labor management representative for distribution to the Union health and safety representative. If you have any questions or need additional information concerning this report, please contact me on 410-965-7462 or Crystal Pauley on 410-966-9369. If you have any other environmental concerns, please contact our **Environmental Hotline** on 410-966-7026.

Attachment: Asbestos Inspection Report for the Poteau FO (E32)

cc:

Selena Gibson, SSA, OLMR

Jamie Bryant, PHS, DFOH (cover only)

Howard Eggerman (cover and Executive Summary only)



FOH

Federal Occupational Health
a component of the US Public Health Service



INITIAL ASBESTOS INSPECTION

POTEAU FIELD OFFICE
SOCIAL SECURITY ADMINISTRATION
1306 TARBY ROAD
POTEAU, OK 74953

SOCIAL SECURITY ADMINISTRATION CODE E32
GSA BUILDING NUMBER OK1489

Survey Date:

DECEMBER 19, 2007

Prepared by:

UNITED STATES PUBLIC HEALTH SERVICE
FEDERAL OCCUPATIONAL HEALTH SERVICE
DALLAS AREA OFFICE
1301 YOUNG STREET, SUITE 772
DALLAS, TX 75202

A. EXECUTIVE SUMMARY

On December 19, 2007 James Fontenarosa, an accredited asbestos inspector representing the U.S. Public Health Service Federal Occupational Health, conducted an initial asbestos inspection at the Poteau Field Office (Social Security Administration Code E32, GSA building number OK1489) located at 1306 Tarby Road in Poteau, OK 74943. The asbestos inspection included the visual examination of all Social Security Administration occupied spaces, mechanical spaces serving the SSA office, bulk sampling suspect materials, and analysis of suspected asbestos-containing building materials identified at the facility. Thirteen building materials suspected of containing asbestos were identified that included: ceiling tile, wallboard, joint compound, wall vinyl base coves and associated adhesives, floor tile and associated mastic, carpet mastic, caulking, sink coating, and pipe putty. Forty-five bulk samples of building materials suspected to contain asbestos were collected during this asbestos inspection. A total of forty-five bulk materials were analyzed. The Federal Occupational Health National Environmental Reference Laboratory in Denver, Colorado analyzed samples for asbestos using polarized light microscopy.

Laboratory analytical results indicated that asbestos was not detected in any of the building materials sampled during this inspection. No further action is necessary.

B. INTRODUCTION

On December 19, 2007 James Fontenarosa, an accredited asbestos inspector representing the U.S. Public Health Service Federal Occupational Health, conducted an initial asbestos inspection at the Poteau Field Office (Social Security Administration Code E32, GSA building number OK1489) located at 1306 Tarby Road in Poteau, OK 74943. The survey included inspection of all SSA occupied spaces in the building and the mechanical spaces serving the SSA office. Prior to the survey, the floor plans were reviewed.

The Poteau Field Office occupies a single-story building. Construction of the building was completed in 2007. The Wichita Falls Field Office occupies approximately 6,250 square feet. The exterior walls are brick. The interior walls are wallboard, vinyl covering, and ceramic. The floors are finished with carpet, resilient tile or ceramic tile. Ceilings are wallboard or a suspended metal-grid with lay-in white panels. The Wichita Falls Field Office employs approximately thirteen people. The building has central air conditioning and heating using a system of ductwork to distribute the supply air to the office areas and return air from the office areas. All SSA occupied spaces were inspected during the survey including the following rooms or areas: Open Work Area, Office Manager's Office, ADP/LAN room, File room, Electrical room, Plumbing/Storage, Janitor room, Men's restroom, Women's restroom, Kitchen, Pantry, Break room, Conference room, Private Interview Office, Mail room, Reception Area, Vestibule, Public Men's Restroom, Public Women's Restroom, and Storage room.

Before conducting the survey, an opening conference was conducted with T Jack Armstrong (Office Manager) to discuss the purpose and procedures of the survey. This facility union representative, Carol Lewis, did not attend the opening conference or observe the initial inspection.

Thirteen building materials suspected of containing asbestos were identified that included: ceiling tile, wallboard, joint compound, wall vinyl base coves and associated adhesives, floor tile and associated mastic, carpet mastic, caulking, sink coating, and pipe putty. Forty-five bulk samples of building materials suspected to contain asbestos were collected during this asbestos inspection. A total of forty-five bulk materials were analyzed. The Federal Occupational Health National Environmental Reference Laboratory in Denver, Colorado analyzed samples for asbestos using polarized light microscopy.

Laboratory analytical results indicated that asbestos was not detected in any of the building materials sampled during this inspection.

C. METHODS

The survey of the facility was performed according to the Social Security Administration's protocol and 40 CFR Part 763 Subpart E (Asbestos-Containing Materials in Schools). This survey also complied with other federal standards and regulations, including those of the Occupational Safety and Health Administration and the Environmental Protection Agency.

Building materials of the same type were grouped building-wide and sampled using a random sampling plan. No outdoor building material samples were collected during this inspection. The samples of the materials were collected after office hours. Sample collection was minimally destructive and samples were collected from inconspicuous areas. The suspect material was thoroughly wetted and all layers of the suspect material were penetrated when taking samples. Samples were placed in sealed containers or bags. After sealing the container, the container surface was wet-wiped. All samples were assigned an identifier as required by Social Security Administration protocol. The floor plan included in this report indicates the locations from which these samples were obtained. Forty-five bulk samples of building materials suspected to contain asbestos were collected during this asbestos inspection. A total of forty-five bulk materials were analyzed.

Samples were analyzed by polarized light microscopy in compliance with guidelines established by the Environmental Protection Agency in its Method for the Determination of Asbestos in Bulk Building Materials (EPA-600/R-93-116) at the U.S. Public Health Service-Federal Occupational Health laboratory in Denver, Colorado. The U.S. Public Health Service-Federal Occupational Health laboratory is currently accredited for bulk asbestos analysis by the National Voluntary Laboratory Accreditation Program of the National Institute of Standards and Technology. Materials were considered to contain asbestos if the sample showed a concentration of asbestos greater than one percent.

The laboratory analysis report may indicate a different sample description color from the color indicated on the chain of custody. The color perceptions in the table relate more to the exterior appearance of the material if it is to be easily identified on site, whereas the color descriptions from the laboratory report refer to the color as it appeared on the microscope sample after preparation for analysis. Any confusion regarding referred material may be removed by looking more closely at material location and sample numbers. Color descriptions may vary with variation in lighting conditions and individual perception.

D. RESULTS

Thirteen building materials suspected of containing asbestos were identified that included: ceiling tile, wallboard, joint compound, wall vinyl base coves and associated adhesives, floor tile and associated mastic, carpet mastic, caulking, sink coating, and pipe putty. Forty-five bulk samples of building materials suspected to contain asbestos were collected during this asbestos inspection. A total of forty-five bulk materials were analyzed. The Federal Occupational Health National Environmental Reference Laboratory in Denver, Colorado analyzed samples for asbestos using polarized light microscopy.

Laboratory analytical results indicated that asbestos was not detected in any of the building materials sampled during this inspection.

E. DISCUSSION AND RECOMMENDATIONS

No asbestos containing building materials were identified during this inspection. No further action is necessary.

F. SUPPORTING DOCUMENTS

The following supporting documents are attached to the report:

Summary Tables of Inspection Results (3 pages)

Photographs (5 pages)

Laboratory Report (12 pages)

Sample Locations Floor Plan (1 page)

Summary of Negative Materials

Room(s)	Location	Material Description	Sample Number (s)	Results
Open Work Area, Office Manager's Office, ADP/LAN room, File room, Electrical room, Plumbing/Storage, Janitor room, Kitchen, Pantry, Break room, Conference room, Private Interview Office, Mail room, Reception Area, Vestibule, and Storage room	Ceilings	2' x 4' White Random Fissure Ceiling Tile	06-0E32-A001B 06-0E32-A002B 06-0E32-A003B 06-0E32-A004B 06-0E32-A005B	None Detected
Open Work Area, Office Manager's Office, ADP/LAN room, File room, Electrical room, Plumbing/Storage, Janitor room, Men's restroom, Women's restroom, Kitchen, Pantry, Break room, Conference room, Private Interview Office, Mail room, Reception Area, Public Men's Restroom, Public Women's Restroom, and Storage room	Walls and Ceilings	Wallboard	06-0E32-A006B 06-0E32-A007B 06-0E32-A008B 06-0E32-A009B 06-0E32-A010B	None Detected
Open Work Area, Office Manager's Office, ADP/LAN room, File room, Electrical room, Plumbing/Storage, Janitor room, Men's restroom, Women's restroom, Kitchen, Pantry, Break room, Conference room, Private Interview Office, Mail room, Reception Area, Public Men's Restroom, Public Women's Restroom, and Storage room	Walls and Ceilings	Joint Compound	06-0E32-A011B 06-0E32-A012B 06-0E32-A013B 06-0E32-A014B 06-0E32-A015B	None Detected
Open Work Area, Office Manager's Office, ADP/LAN room, File room, Electrical room, Plumbing/Storage, Janitor room, Conference room, Private Interview Office, Mail room, and Storage room	Walls	4" Brown Wall Vinyl Base Cove	06-0E32-A016B 06-0E32-A017B 06-0E32-A018B	None Detected

Summary of Negative Materials (continued)

Room(s)	Location	Material Description	Sample Number (s)	Results
Open Work Area, Office Manager's Office, ADP/LAN room, File room, Electrical room, Plumbing/Storage, Janitor room, Conference room, Private Interview Office, Mail room, and Storage room	Walls	Adhesive associated with 4" Brown Wall Vinyl Base Cove	06-0E32-A019B 06-0E32-A020B 06-0E32-A021B	None Detected
Kitchen, Pantry, and Break room	Walls	4" Dark Brown Wall Vinyl Base Cove	06-0E32-A022B 06-0E32-A023B 06-0E32-A024B	None Detected
Kitchen, Pantry, and Break room	Walls	Adhesive associated with 4" Dark Brown Wall Vinyl Base Cove	06-0E32-A025B 06-0E32-A026B 06-0E32-A027B	None Detected
ADP/LAN room, File room, Electrical room, Plumbing/Storage room, Janitor room, Mail room and Storage room	Floors	12" x 12" Brown Floor Tile	06-0E32-A028B 06-0E32-A029B 06-0E32-A030B	None Detected
ADP/LAN room, File room, Electrical room, Plumbing/Storage room, Janitor room, Mail room and Storage room	Floors	Mastic associated with 12" x 12" Brown Floor Tile	06-0E32-A031B 06-0E32-A032B 06-0E32-A033B	None Detected
Open Work Area, Office Manager's Office, File room, Conference room, and Private Interview Office	Floors	Carpet Mastic	06-0E32-A034B 06-0E32-A035B 06-0E32-A036B	None Detected
Open Work Area, Office Manager's Office Men's restroom, Women's restroom, Private Interview Office, Reception Area Public Men's Restroom, Public Women's Restroom	Windows/Fixtures	Caulking, White	06-0E32-A037B 06-0E32-A038B 06-0E32-A039B	None Detected
Kitchen	Sink	Sink Coating	06-0E32-A040B 06-0E32-A041B 06-0E32-A042B	None Detected

Summary of Negative Materials (continued)

Room(s)	Location	Material Description	Sample Number (s)	Results
Plumbing/Storage	Pipe	Pipe Putty	06-0E32-A043B 06-0E32-A044B 06-0E32-A045B	None Detected



Federal Occupational Health Service
PO Box 25145
Bldg 41, Ent E-1, Rm 190
Denver Federal Center
Denver Co 80225-0145
Phone: 303-236-0076 x 603
Fax: 303-236-3440

January 15, 2008

LGN B0888891

Alex Fontenarosa
Federal Occupational Health
1301 Young Street, Suite 772
Dallas, TX 75202

Dear Mr. Fontenarosa:

Enclosed are the results of the analysis of 45 bulk materials from Social Security Administration field office E32, Poteau OK, submitted to the Division of Federal Occupational Health (DFOH) National Environmental Reference Laboratory (NERL) Asbestos/Fine Particle Analytical Division in Denver, Colorado, for asbestos analysis. These samples were received at NERL on December 23, 2007. The methods used for this evaluation involve stereo- and polarized-light microscopy (PLM) in compliance with guidelines established by EPA in its Method For The Determination Of Asbestos In Bulk Building Materials (EPA-600/R-93-116). The DFOH laboratory services are currently accredited for bulk asbestos analysis by the National Voluntary Laboratory Accreditation Program (NVLAP) of the National Institute of Standards and Technology (NIST). This report may not be used to claim product endorsement by NVLAP or other U.S. Government agency. This report may not be reproduced except in full, without the written approval of NERL. Our NVLAP laboratory code number is 101593-0.

The results given, which pertain only to the materials submitted for testing, are listed in Table 1. Details of this report will not be issued to any person or agency not associated with you or the SSA. The EPA method guidelines were developed for use in evaluating friable materials. Point-count reanalysis of materials is recommended to confirm trace or low-percentage PLM results. If you have questions regarding the content of this report, analytical procedures or methods, asbestos evaluation or abatement, please contact NERL directly at (303) 236-3455 ext 603.

LABORATORY COORDINATOR

MARK A. STEINER MS
Geologist/Microscopist

LABORATORY DIRECTOR

BRUCE HILLS, MS CSP
Certified Industrial Hygienist

TABLE 1

DIVISION OF FEDERAL OCCUPATIONAL HEALTH
 NERL/AFPAD POLARIZED LIGHT MICROSCOPY (PLM) BRANCH

LGN: B0888891

PROJECT I.D.: Social Security Administration
 Field Office E32, 1306 Tarby Road
 Poteau, Oklahoma

REPORT DATE: January 14, 2008

NVLAP LAB CODE: 101593-0

SAMPLE NUMBER	ASBESTOS PRESENT?	-----Estimated % Composition-----		
		ASBESTIFORM MINERAL FIBERS	OTHER FIBROUS CONSTITUENTS	TOTAL % ASBESTOS
06-0E32-A001B: Ceiling Tile: off/white, heterogeneous, friable, fibrous	No	None Detected	Cellulose 40 Fibrous Glass 20	0
06-0E32-A002B: Ceiling Tile: off/white, heterogeneous, friable, fibrous	No	None Detected	Cellulose 40 Fibrous Glass 20	0
06-0E32-A003B: Ceiling Tile: off/white, heterogeneous, friable, fibrous	No	None Detected	Cellulose 40 Fibrous Glass 15	0
06-0E32-A004B: Ceiling Tile: off/white, heterogeneous, friable, fibrous	No	None Detected	Cellulose 40 Fibrous Glass 20	0
06-0E32-A005B: Ceiling Tile: tan/white, heterogeneous, friable, fibrous	No	None Detected	Cellulose 40 Fibrous Glass 15	0
09-0E32-A006B: Wall Board: white/tan, heterogeneous, friable, nonfibrous	No	None Detected	Cellulose 17 Fibrous glass 3	0
09-0E32-A007B: Wall Board: white/tan, heterogeneous, friable, nonfibrous	No	None Detected	Cellulose 7 Fibrous glass 3	0

TABLE 1
(CONTINUED)

SAMPLE NUMBER	ASBESTOS PRESENT?	-----Estimated % Composition-----		
		ASBESTIFORM MINERAL FIBERS	OTHER FIBROUS CONSTITUENTS	TOTAL % ASBESTOS
09-0E32-A008B: Wall Board: white, homogeneous, friable, nonfibrous	No	None Detected	Fibrous glass 3	0
09-0E32-A009B: Wall Board: white, homogeneous, friable, nonfibrous	No	None Detected	Fibrous glass 1	0
09-0E32-A010B: Wall Board: white/tan, heterogeneous, friable, nonfibrous	No	None Detected	Cellulose 32 Fibrous glass 3	0
09-0E32-A011B: Compound/Paint: white/green, heterogeneous, friable, nonfibrous	No	None Detected	None	0
09-0E23-A012B: Compound: white, homogeneous, friable, nonfibrous	No	None Detected	None	0
09-0E32-A013B: Compound/Paint: white/tan, heterogeneous, friable, nonfibrous	No	None Detected	None	0
09-0E32-A014B: Compound/Paint: white/tan, heterogeneous, friable, nonfibrous	No	None Detected	None	0
09-0E32-A015B: Compound/Paint: white/tan, heterogeneous, friable, nonfibrous	No	None Detected	None	0
09-0E32-A016B: Base Cove: beige, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A019B: Adhesive: white, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0

TABLE 1
(CONTINUED)

SAMPLE NUMBER	ASBESTOS PRESENT?	-----Estimated % Composition-----		
		ASBESTIFORM MINERAL FIBERS	OTHER FIBROUS CONSTITUENTS	TOTAL % ASBESTOS
09-0E32-A017B: Base Cove: beige, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A020B: Adhesive: white, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A018B: Base Cove: beige, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A021B: Adhesive: white, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A022B: Base Cove: maroon, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A025B: Adhesive: white, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A023B: Base Cove: maroon, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A026B: Adhesive: white, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A024B: Base Cove: maroon, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A027B: Adhesive: white, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0

TABLE 1
(CONTINUED)

SAMPLE NUMBER	ASBESTOS PRESENT?	-----Estimated % Composition-----		TOTAL % ASBESTOS
		ASBESTIFORM MINERAL FIBERS	OTHER FIBROUS CONSTITUENTS	
09-0E32-A028B:	No			
Floor Tile: light brown, homogeneous, nonfriable, nonfibrous		None Detected	None	0
09-0E32-A031B:	No			
Adhesive: yellow, homogeneous, nonfriable, nonfibrous		None Detected	None	0
09-0E32-A029B:	No			
Floor Tile: light brown, homogeneous, nonfriable, nonfibrous		None Detected	None	0
09-0E32-A032B:	No			
Adhesive: clear tan, homogeneous, nonfriable, nonfibrous		None Detected	None	0
09-0E32-A030B:	No			
Floor Tile: light brown, homogeneous, nonfriable, nonfibrous		None Detected	None	0
09-0E32-A033B:	No			
Adhesive: clear tan, homogeneous, nonfriable, nonfibrous		None Detected	None	0
09-0E32-A034B:	No			
Adhesive: pale yellow, homogeneous, nonfriable, nonfibrous		None Detected	None	0
09-0E32-A035B:	No			
Adhesive: pale yellow, homogeneous, nonfriable, nonfibrous		None Detected	None	0
09-0E32-A036B:	No			
Adhesive: pale yellow, homogeneous, nonfriable, nonfibrous		None Detected	Synthetics 1	0

TABLE 1
(CONTINUED)

SAMPLE NUMBER	ASBESTOS PRESENT?	-----Estimated % Composition-----		
		ASBESTIFORM MINERAL FIBERS	OTHER FIBROUS CONSTITUENTS	TOTAL % ASBESTOS
09-0E32-A037B: Caulk: white, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A038B: Caulk: white, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A039B: Caulk: white, homogeneous, nonfriable, nonfibrous	No	None Detected	None	0
09-0E32-A040B: Coating: light gray, homogeneous, nonfriable, nonfibrous	No	None Detected	Cellulose 10	0
09-0E32-A041B: Coating: light gray, homogeneous, nonfriable, nonfibrous	No	None Detected	Cellulose 10	0
09-0E32-A042B: Coating: light gray, homogeneous, nonfriable, nonfibrous	No	None Detected	Cellulose 10	0
09-0E32-A043B: Packing: light green, homogeneous, nonfriable, nonfibrous	No	PIPE PUTTY None Detected	None	0
09-0E32-A044B: Packing: light green, homogeneous, nonfriable, nonfibrous	No	PIPE PUTTY None Detected	None	0
09-0E32-A045B: Packing: light green, homogeneous, nonfriable, nonfibrous	No	PIPE PUTTY None Detected	None	0

END OF DOCUMENT

NATIONAL ENVIRONMENTAL HEALTH EFFECTS LABORATORY

Building #1, Room 190, P.O. Box 25145
 Denver Federal Center
 Denver, CO 80226-0145

Tel: (303)-236-3425 ext. 603 Fax: (303)-236-3440

Attn: Mark Steiner

PROJECT REFERENCE

Agreement No.: A115852
 Statement of Work No.: S115854
 Project No.: P128982

Agency/Project: SSA
 Name: PotEAU FO (E32)
 Location: 1306 Tarby Rd.
 (City, State): Poteau, OK 74953

Address: 1901 Young St., Suite 772
 Dallas, TX 75202

Phone/Fax: 214-767-2677 / 214-767-0002

Email: mfontenarosa@epsc.gov

FOR Lab Use Only

Project / Report #: A115852
 Due Date: 12-20-07

Samples Received Chilled? YES (NO Vehicle one)

Container Types: P-Pestic, G-Gases, V-VOC
 Preservatives: A-Toluene, B-H₂SO₄, C-HNO₃, D-NaOH

STD - Standard
 R - Rush
 2d - Two Day Rush
 ND - Next Day Rush
 SD - Same Day Rush
 WH - Weekend/Holiday

60888889
 Received with Name & Date
 1/4/08

ID #	Type	Media	Collected		Sample Location / Description	Air			Water			Turn Around Time	Lab ID #
			Date	Time		Flow (PM)	Time (min)	Volume (liters)	Area (in ²)	Volume (liters)	Code		
08-0E32-A001B	6		12/11-07	11:00	2nd Random Inside Gully, T/W CT1 RM20-56 Area							STD	PLM
A002B	6				NE Area RM3 - Entrance							STD	PLM
A003B	6				RM4 - SW Area							STD	PLM
A004B	6				RM1, East Area							STD	PLM
A005B	6				RM6, SE Area							STD	PLM
A006B	6				Mailbox RM20, SC Area							STD	PLM
A007B	6				RM3, NE Area							STD	PLM
A008B	6				RM4, SW Area							STD	PLM

- ANALYSIS CODES:**
- 1-Air 2-Water 3-Paint 4-Soil 5-Dust
 - 3-Soil 7-Water 8-Contact Plate
 - 21-Tape 10-Spore Trap (Zelon & others)
 - 1-Other

- SAMPLE MEDIA CODES:**
- 1-Charcoal 2-XAD 3-Standard Weigh
 - 4-Preweighed 5-MEA 6-CCA 7-R2A/ATSA
 - 8-Air-C-Cell Cassette 9-MCE Cassette (0.45)
 - 10-MCE Cassette (0.8) 11-MCE Filter 12-Other

COMMENTS:
 Applied to non-viable microbiological samples only. Applied to asbestos samples, SD: 2-hour PLM/PCM, 8-hour TEM; ND: 24-hour; R: 3-5 business days.

Building 41, Room 189, POB 26145
 Denver Federal Center
 Denver, CO 80226-0145

Tel: (303) 236-3466 ext. 803 Fax: (303) 236-3440

Attn: Mark Steinar

Name: Alex Fontenrosa
 Address: 1301 Young St., Suite 772
 Dallas, TX 75202

Phone/Fax: 214-767-3677 / 214-767-0002

Email: alexfontenrosa@epc.gov

Agreement No.: A115852

Statement of Work No.: S115854

Project No.: P128982

Agency/Project: SSA

Name: PotEAU FC (E32)

Location: 1308 Tarby Rd.

{City, State}: PotEAU, OK 74853

For Lab Use Only
 Project / Report #: 19288891
 Due Date: 10/28/08
 Condition on Receipt with Name & Date

Samples Received Chilled? YES NO (circle one)

Container Types:
 P-Plastic, G-Glass, V-VOC
 Preservatives:

A-More, B-H₂SO₄,
 C-HNO₃, D-MeOH

STD - Standard

R - Rush

2D - Two Day Rush

ND - Next Day Rush

SD - Same Day Rush

WH - Weekend/Holiday

ID #	Type	Media	Collected		Sample Location / Description	Air			Turn Around Time*	Lab ID #	
			Date	Time		Flow (CFM)	Time (Min)	Volume (Liters)			Wipe Area (in ²)
06-0E32-A009B	6		12-11-07	11:00	Wallboard RMS, NE Area					STD	PLM
A010B	6				↓ RMB, SE Area					STD	PLM
A011B	6				Joint Compound RMB, SE Area					STD	PLM
A012B	6				RN3, NE Area					STD	PLM
A013B	6				RMB, SW Area					STD	PLM
A014B	6				RMS, NE Area					STD	PLM
A015B	6				RMB, SE Area					STD	PLM
A016B	8				4" Brown Insul facing pour RM 28, NE Area					STD	PLM

1-Air 2-Water 3-Paint 4-Soil 5-Dust
 6-Bulk 7-Wipe 8-Container Filter
 9-Tape 10-Spore Trap (Zefon & others)
 11-Other

1-Charcoal 2-XAD 3-Method Weight
 4-Fresnel Light 5-HEPA 6-CCA 7-R2M/RTSA
 8-Air-O-Cell Cassette 9-AMCE Cassette (0.45)
 10-AMCE Cassette (0.8) 11-ACE Filter 12-Other

COMMENTS:
 Applied to non-wable microbiological samples only. Applied to asbestos samples. SD: 2-hour PLM/PCM, 6-hour TEM. ND: 24-hour. R: 3-5 business days.

12-2-07
 NGAL
 1/16/08

OSHA-307 (REV. 12-13-81) FEDERAL OCCUPATIONAL SAFETY AND HEALTH DIVISION, OSHA-307 (REV. 12-13-81)

Building 41, Room 180, POB 26148
 Denver Federal Center
 Denver, CO 80226-0148
 Tel: (303) 235-3468 ext. 603 Fax: (303) 235-3440
 Alt: Mark Steiner

Agreement No.: A115852
 Statement of Work No.: S115854

Project No: P158982
 Agency/Project: SSA

Name: Alex Fortenarosa
 Address: 1301 Young St, Suite 712
 Dallas, TX 76202

Phone/Fax: 214-367-3677 / 214-767-0092
 Email: afortenarosa@opsc.gov

Location: 1306 Tarby Rd.
 (City, State): Poteau, OK 74953

For Lab Use Only
 Project/Report #: P158982
 Date: 12-20-08
 Samples Received Cooled? YES NO (circle one)

Container Types: P-Plastic, G-Glass, V-VOC
 Preservatives: A-None, B-H2SO4, C-HNO3, D-NaOH
 STD - Standard
 R - Rush
 2D - Two Day Rush
 ND - Next Day Rush
 SD - Same Day Rush
 WH - Weekend/Holiday

ID#	Type	Media	Sample		Sample Location / Description	Air			Turn Around Time ¹	Lab ID #	
			Collected Date	Time		Flow (LPM)	Time (min.)	Volume (Liters)			Wipe Area (ft ²)
08-0E32-A017B	6		12-10-08	16:00	4" Brown wall over Vinyl wall RM3, NW Area					STD	PLM
A018B	6				4" Brown wall over Vinyl wall RM1, NE Area					STD	PLM
A019B	6				Vinyl w/str. w/ wall RM 20, NE Area					STD	PLM
A020B	6				RM3, NW Area					STD	PLM
A021B	6				RM13, NE Area					STD	PLM
A022B	8				4" DK Brown wall over Vinyl wall RM10, NW Area					STD	PLM
A023B	8				RM12, NW Area					STD	PLM
A024B	6				RM12, SW Area					STD	PLM

1-Air 2-Water 3-Paint 4-Soil 5-Dust
 6-Sulk 7-Wipe 8-Contact Plate
 9-Tape 10-Spore Trap (Zelon & others)
 11-Other
 L-Chemical 2-XAD 3-Standard Weight
 4-Pre-weighed S-MEA 6-COA 7-R2A/TS4
 8-Air-Cell Cassette 9-ACE Cassette (0.45)
 10-ACE Cassette (0.8) 11-MOE Filter 12-Other

12-20-08
 M. Steiner
 1/16/08

* Applied to non-viable microbiological samples only. * Applied to asbestos samples. SD: 2-hour PLM/PCMA, 8-hour TEM. ND: 24-hour. R: 3-5 business days.

2017 OFFICE HEALTHY ENVIRONMENT FEDERAL BUDGET NATIONAL HEALTH TRAINING PROGRAM FIELD DATA SHEET

Building 41, Room 190, POB 25145
 Denver Federal Center
 Denver, CO 80225-0145

Tel: (303)-236-3486 ext. 603 Fax: (303)-236-3440

Attn: Mark Stehler

Name: Alex Fontenarosa
 Address: 1301 Young St., Suite 772
 Dallas, TX 75202

Phone/Fax: 214-767-9677 / 214-767-9002
 Email: afontenarosa@epa.gov

Agreement No.: A115852

Statement of Work No.: S415854

Project No: P128982

Agency/Project: SSA

Name: Poteau FO (E32)

Location: 1308 Tarby Rd.

(City, State): Poteau, OK 74953

For Lab Use Only
 Project Report #: B888827
 Due Date: 12-20-07
 Samples Received Chilled? YES NO (circle one)

Container Types:
 P-Plastic, G-Glass, V-VOC
 Preservatives:
 A-None, B-H₂SO₄,
 C-HNO₃, D-NaOH

STD - Standard
 R - Rush
 2D - Two Day Rush
 ND - Next Day Rush
 SD - Same Day Rush
 WH - Weekend/Today

ID #	Type	Media*	Sample		Sample Location / Description	AIR			Turn Around Time*	Lab ID #							
			Collected Date	Time		Flow (LPM)	Time (min.)	Volume (liters)			Wipes Area (m ²)	Water Volume (liters)					
06-DE32-A025B	6		12/17/07	10:10	4x OK wall cov Vintl Mstc, Wmbr Rm10, New Area												
A026B	6				Rm12, Wb Area												
A027B	6				Rm12, SW Area												
A028B	6				12X12 Brown Floor Tile, FT1 Rm20, NE Area												
A029B	6				Rm3, SE Area												
A030B	6				Rm15, SE Area												
A031B	6				12X12 Brown Floor Tile, FT1 Rm20, NE Area												
A032B	6				Rm3, SE Area												

- 1-Air 2-Water 3-Paint 4-Soil 5-Dust
- 6-Bulk 7-Wipe 8-Contact Plate
- 9-Tape 10-Spore Trap (Zeion & others)
- 11-Other

- 1-Charcoal 2-XAD 3-Minuted Weight
- 4-Preweighed 5-AEA 6-CCA 7-R2A/TSA
- 8-Air-O-Cell Cassette 9-ACE Cassette (OAS)
- 10-MCE Cassette (OAS) 11-ACE Filter 12-Other

12-20-07
 MSL
 New Area

12-20-07
 MSL
 New Area
 1/16/08

* Applied to non-viable microbiological samples only. * Applied to asbestos samples. SD: 2-hour PLM/PCM, 6-hour TEM; ND: 24-hour; R: 3-5 business days.

NATIONAL ENVIRONMENTAL HEALTH EFFECTS RESEARCH LABORATORY
 Building 41, Room 160, POB 25145
 Denver Federal Center
 Denver, CO 80225-0145
 Tel: (303) 236-3456 ext. 603 Fax: (303) 236-3440
 Attn: Mark Steiner

Agreement No.: A115852
 Statement of Work No.: S115854
 Project No: P 128982
 Agency/Project: SSA
 Name: PotEAU FO (E32)
 Location: 1306 Tardy Rd.
 (City, State): PotEAU, OK 74953

For Lab Use Only
 Project/Report #: B5888891
 Due Date:
 Samples Received Chilled? YES NO (circle one)
 Containers Types:
 P-Plastic, G-Glass, V-VOC
 Preservatives:
 A-Nona, B-H₂SO₄,
 C-HNO₃, D-NaOH

Name: Alex Fortenaro
 Address: 1301 Young St., Suite 772
 Dallas, TX 75202
 Phone/Fax: 214-767-3577 / 214-767-0002
 Email: afortenaro@epsc.gov

ID #	Type	Medium	Collected		Sample Location / Description	Air			Turn Around Time*	Lab ID #
			Date	Time		Flow (LPM)	Time (Min.)	Volume (Liters)		
06-0E32-A033B	6		12/11/07	11:00	12x12 Groom Floor Tg, Washc, FTW1 RM 15, SE Area				STD	PLM
A034B	6				Carpet Washc, CM, RM, East Hall				STD	PLM
A035B	6				RM 1, West Area				STD	PLM
A036B	6				RM 1, South Area				STD	PLM
A037B	6				Colking, White, CK1 North Area				STD	PLM
A038B	6				RM 8, West Area				STD	PLM
A039B	6				RM 18, SE Area				STD	PLM
A040B	6				Sink Laundry, grey, SK1 RM 10 North Area				STD	PLM

1-Chloroal 2-XAD 3-Methanol Weight
 4-Fenethylal 5-MEA 6-CGA 7-R28TSA
 8-Ali-O-Cell Cassette 9-ACE Cassette (QAS)
 10-ACE Cassette (Q8) 11-ACE Filter 12-Chair

COMMENTS: 12/20/07
 1/15/08

* Applied to non-viable microbiological samples only. * Applied to asbestos samples. SO: 2-hour PLM/PCM, 6-hour TEM; ND: 24-hour; R: 3-5 business days.